



Technical Data Sheet

# Ramping Compound

## General Purpose Polymer Modified Concrete



### Product

Ramping Compound is a general purpose polymer modified micro concrete with some flowing characteristics. Ramping Compound is a blend of Portland Cement graded aggregates and chemical additives to provide a strong cementitious compound with minimal shrinking or cracking.

### Description

Ramping Compound is a ready to use dry powder requiring the addition of a controlled amount of clean water to produce a workable consistency for shaping or patching work in domestic or industrial applications.

Higher performance to bond and strength may be gained by the addition of Sure Prime 644 Acrylic Liquid.

### Recommended Uses

- Repairs to damaged concrete -either permanent or temporary.
- Where some adhesive properties of the repair medium are required.
- Applied from 5.0mm to 150mm thickness in a single application.
- For internal or external use.
- High Strength option available with Sure Prime 644 Acrylic Liquid addition.

### Features & Benefits

- Single or two component material with high compressive strength.
- Rapid curing.
- Can be applied directly onto prepared concrete substrates for temporary service.
- Adheres to prepared concrete surfaces with excellent adhesion to prepared and primed surfaces
- Durable with high build characteristics
- Eliminates the need for separate sand and cement screeds.

### Performance Properties

#### Typical Compressive Strength

Tested in accordance with AS1012.9 at 20°C

Age	Compressive Strength
1 day	>5-10 Mpa
28 days	>30-40 Mpa

#### Typical Working Time

Temperature	Time (minutes)
20°C	30-40 minutes
30°C	20-30 minutes

**Note:** Performance time will be influenced by the desired consistency of the compound. A more fluid compound will achieve the lower range of strength and the upper range in set and working time.

#### Typical Setting Times

Vicat setting times 20°C

Initial Set	20°C	45-90 minutes
	30°C	30-60 minutes

#### Coverage & Liquid Requirement

For screeding characteristics use 1 litre of Sure Prime 644 with the addition of 1.4 - 1.8 litres of clean water.

For flowable characteristics, use approximately 1 litre of Sure Prime 644 with 2.5 litres per 20kg bag.

### Packaging

Ramping Compound is supplied in a 20kg polylined bag.

### Application Instructions

#### Surface Preparation

The surface of the substrate should be sound and clean and free of loose dust. While Ramping Compound will achieve reasonable bond to prepared surfaces without priming, priming with Surecure Primer will greatly increase bond where permanent fixing is required. Well bonded Ramping Compound to prepared substrates will still provide a sound surface should fine cracks occur through temperature or drying shrinkage stress.

#### Mixing

Ramping Compound requires a measured quantity of clean water and Sure Prime 644 to provide a smooth workable compound to suit the application.

Excessive water will increase shrinkage potential and reduce ultimate strength. Mixing should be by adding the powder compound to the water and preferably thoroughly mixed with a mechanical high shear stirrer.

#### Application of Coating

Ramping Compound when compacted and cured will exhibit similar durability characteristics to high strength concrete of 30-40 mpa grade. Ramping Compound can be coated with any system that adheres to a cement bound compound or concrete.

#### Storage

Ramping Compound has a shelf life of approximately 8 months if kept in a dry environment completely away from moisture.

#### Clean Up

Ramping Compound should be removed from tools and equipment with clean water immediately after use.

### Health and Safety

This product is classified as hazardous according to criteria of Work Safe Australia. Material containing Portland Cement and sand now fall into this category. Continuous or extended contact with this product may cause irritation as well as respiratory issues such as bronchitis or silicosis.

- During use avoid inhalation of dust, contact with skin and eyes.
- Suitable protective clothing, dust masks, gloves and eye protection should be worn.
- Continual or extended contact with cement products can cause skin irritation.
- If skin irritation occurs, remove contaminated clothing and flush skin thoroughly with water for a minimum of 15 minutes. Contact Poisons Information Centre or consult medical adviser.
- Material Safety Data Sheets (MSDS) are available on request from the office. Read the MSDS and product data sheet carefully before using any product.

### Disclaimer

Please Note: Recommendation and advice regarding the use of this product is to be taken as a guide only and Sure Level Pty. Ltd. shall not be liable for any inaccuracy in the information or for any loss, injury or damage whatsoever resulting from its use. To the full extent permitted by law, Sure Level Pty. Ltd. liability is limited at its discretion, to the replacement of the goods or the supply of equivalent goods.

### Fire

Ramping Compound is non flammable.

### Part Number

SLF 3008

### Contact

Sure Level Pty Ltd  
12 Northgate Drive  
Thomastown Vic 3074 Australia Phone: + 61 3 9464 5753 Fax: + 61 3 9464 3630 Web:  
www.surelevel.com.au  
Email: info@surelevel.com.au

Date of Issue: 26 July 2010

